

Serial No. 09/427,050
Filed: October 25, 1999
Examiner: R. Sargent
Group Art Unit: 1711

9. (Amended) A composition according to claim 1, comprising from about 5-35%, based on the weight of the composition, of the auxiliary polyether or polyester polyol, or a mixture thereof.

34. (Twice amended) A method for preparing a phthalate polyester-ether polyol comprising forming an intermediate phthalate-diethylene glycol polyester-polyol comprising

(a) about 2-60% by weight of phthalic anhydride or phthalic acid; and

(b) about 40-98% by weight of diethylene glycol; and

alkoxylating the intermediate phthalate-diethylene glycol polyester polyol with about 55-80% of propylene oxide based on the weight of the phthalate polyester-ether polyol.
